

TECHNICAL DATA

REGUPOL EVERROLL

IMPACT 12 + 4 mm



Properties	Standard	Result
Material		Base layer: Components made of synthetic rubber (SBR), PUR binder Wear layer: Components made of synthetic rubber (EPDM), PUR binder
Thickness		12 mm base layer + 4 mm wear layer
Dimensions		Rolls, length 40 m natural, 20 m sealed, width 1.25 m
Weight		Base layer: approx. 6.8 kg/m ² or 0.68 kg/m ² /mm Wear Layer: ultimate approx. approx. 5.5 kg/m ² or 1.38 kg/m ² /mm
Force reduction	internal test based on EN 14904	approx. 38 %
Impact resistance	based on EN 14904 / EN 1517	> 21 Nm
Slip resistance	AS 4586:2013 Slip resistance classification of new pedestrian surface materials, Appendix A – Wet Pendulum Test	Ultimate Natural: P4 Ultimate Sealed: P2
Caloric conductivity	EN 12664	λ 0.133 (W/m*K)
Electrostatic behaviour	EN 1815:2016	≤ 2 kV / antistatic
Colour fastness	ISO 105 – B02:2002	Blue scale: level 5 Grey scale: level 4
Temperature resistance	In-house testing	-40 to +90 °C
Salt water resistance	based on DIN EN ISO 175	resistant
Formaldehyde emission		class E1

Should any questions arise that need clarification, contact your sales representative at our company directly or write to us using the contact form on our website www.regupol.com.au

Please request a product sample from your **REGUPOL** team before making a decision. The **REGUPOL everroll** rubber flooring is made from recycled materials, variations in the shading, EPDM and colour chip dispersion is normal.

We reserve the right to make alterations to the technical data. All information is subject to fluctuation tolerances of ± 10 %. To verify the accuracy of the contents, please refer to the information on our website www.regupol.com.au

